



# Chloroseal

Property/Test	Standard	ASTM D2000 Std.	Result
Durometer, Shore A	ASTM D2240	70 (+/-5)	71
Tensile Strength	ASTM D412	min 7.0 MPa	11.7 MPa
Elongation	ASTM D412	min 250%	312%
Heat Resistance Change in hardness Change in tensile strength Change in ultimate elongation	ASTM D573 70h @ 70C	+/- 15 max points +/- 30 max points -50 % max	+2 points -8 points -17%
Chloramine Resistance Change in hardness, Shore A Volume change	ASTM D6284 Immersion in 50ppm Chloramines 672h @ 70C	ASTM D6284 +/- 4 max points +/- 20% max	+1 points +1.9%

Properties are typical values. Final determination for suitability for use must be made by the customer (09/14)