



# EPDM Closed Cell Sponge Spec Sheet

RubberMill Part No.	RCC13S3B	RCC13M3B	RCC13F3B
Density	4.5-7 pcf	9-14 pcf	16-25 pcf
Compression Deflection (@25% Deflection)	2-5 psi	5-9 psi	9-13 psi
Water Absorption (By Weight)	5%	5%	5%
Temperature Range	-90° F to 275° F	-90° F to 275° F	up to 300° F
Weather Resistance Ozone UV Ozone	Excellent Excellent	Excellent Excellent	Excellent Excellent
Tensile Strength (Typical)	60 psi	65 psi	110 psi
Elongation (Typical)	125%	180%	200%
Flammability Specifications FMVSS302	Pass	Pass	Pass
Compliance Specifications ASTM D-1056-00 SAE J18-02	2A1 2A1	2A2 2A2	2A3 —

Properties are typical values. Final determination for suitability for use must be made by the customer. (03/17)