



Silicone Foam

Typical Properties of Silicone Foam	
RubberMill Part No.	RFO14W13
Density	13 pcf
Compression (@25% Deflection)	3 psi
Compression (@ 158° F (70°C), 22hrs)	
Water Absorption	3.5%
Temperature Range	-67° F to 392° F
Tensile Strength (min)	35 psi
Elongation	90%
Compression Set 50%	24%
Flammability Specifications	UL94 V-0, HF-1
Color	White

Properties are typical values. Final determination for suitability for use must be made by the customer. (03/17)