



Neoprene Spec Sheet

| RubberMill Part No. | RCC11S3B | RCC11M3B | RCC11F3B |
|--|-------------------|-------------------|-------------------|
| Density | 7-13 pcf | 8-14 pcf | 12-20 pcf |
| Compression Deflection (@25% Deflection) | 2-5 psi | 5-9 psi | 9-13 psi |
| Water Absorption (By Weight) | 5% | 5% | 5% |
| Temperature Range | -70°F to 200°F | -70°F to 200°F | -70°F to 200°F |
| Weather Resistance Ozone UV Ozone | Excellent Fair | Excellent Fair | Excellent Fair |
| Tensile Strength (Typical) | 60 psi | 70 psi | 80 psi |
| Elongation (Typical) | 150% | 130% | 100% |
| Fuel B Resistance | 250% | 250% | 150% |
| Flammability Specifications FMVSS302 | Pass | Pass | Pass |
| Compliance Specifications ASTM D-1056-00 SAE J18 | 2C1 2C1 | 2C2 2C2 | 2C3 2C3 |

Properties are typical values. Final determination for suitability for use must be made by the customer. (09/12)