



# Viton Black Spec Sheet

RubberMill Part No.	RCC16X2B
Density	10-19 lb/ft3 *
Compression Deflection (@25% Deflection – Original)	3.5-6.5 psi *
Compression Deflection (@25% Deflection – 7 Days @ 400° F)	3.5-6.5 psi *
Compression Set (22 Hours @ 75° F)	17%-27% *
Compression Set (22 Hours @ 158° F)	100%
Water Absorption (% Weight Gain)	.00%-.06% *
Temperature Range	-10° F to 400° F
Low Temperature Brittleness	-10° F

Properties are typical values. Final determination for suitability for use must be made by the customer. (09/13)