

EPDM Closed Cell Sponge Spec Sheet

| RubberMill Part No. | RCC13S3B | RCC13M3B | RCC13F3B |
|---|------------------------|------------------------|------------------------|
| Density | 4.5-7 pcf | 9-14 pcf | 16-25 pcf |
| Compression Deflection (@25% Deflection) | 2-5 psi | 5-9 psi | 9-13 psi |
| Water Absorption (By Weight) | 5% | 5% | 5% |
| Temperature Range | -90° F to 275° F | -90° F to 275° F | up to 300° F |
| Weather Resistance Ozone UV Ozone | Excellent Excellent | Excellent Excellent | Excellent Excellent |
| Tensile Strength (Typical) | 60 psi | 65 psi | 110 psi |
| Elongation (Typical) | 125% | 180% | 200% |
| Flammability Specifications FMVSS302 | Pass | Pass | Pass |
| Compliance Specifications ASTM D-1056-00 SAE J18-02 | 2A1 2A1 | 2A2 2A2 | 2A3 — |

Disclaimer: Properties are typical values based on information supplied by material manufacturers. RubberMill is not responsible for errors, omissions and updates. Final determination for suitability for use must be made by the customer.