

Neoprene Spec Sheet

RubberMill Part No.	RCC11S3B	RCC11M3B	RCC11F3B
Density	7-13 pcf	8-14 pcf	12-20 pcf
Compression Deflection (@25% Deflection)	2-5 psi	5-9 psi	9-13 psi
Water Absorption (By Weight)	5%	5%	5%
Temperature Range	-70°F to 200°F	-70°F to 200°F	-70°F to 200°F
Weather Resistance Ozone UV Ozone	Excellent Fair	Excellent Fair	Excellent Fair
Tensile Strength (Typical)	60 psi	70 psi	80 psi
Elongation (Typical)	150%	130%	100%
Fuel B Resistance	250%	250%	150%
Flammability Specifications FMVSS302	Pass	Pass	Pass
Compliance Specifications ASTM D-1056-00 SAE J18	2C1 2C1	2C2 2C2	2C3 2C3

Disclaimer: Properties are typical values based on information supplied by material manufacturers. RubberMill is not responsible for errors, omissions and updates. Final determination for suitability for use must be made by the customer.