

# Viton Black Spec Sheet

RubberMill Part No.	RCC16X2B
Density	10-19 lb/ft3 *
Compression Deflection (@25% Deflection – Original)	3.5-6.5 psi *
Compression Deflection (@25% Deflection – 7 Days @ 400° F)	3.5-6.5 psi *
Compression Set (22 Hours @ 75° F)	17%-27% *
Compression Set (22 Hours @ 158° F)	100%
Water Absorption (% Weight Gain)	.00%-.06% *
Temperature Range	-10° F to 400° F
Low Temperature Brittleness	-10° F

Disclaimer: Properties are typical values based on information supplied by material manufacturers. RubberMill is not responsible for errors, omissions and updates. Final determination for suitability for use must be made by the customer.